

FILTER SAND AND GRAVEL

Highly spherical shape and uniform grading provide filter sand and gravel with reliable performance. Low soluble impurities limits undesirable mineral leaching into the process stream.

ADVANTAGES

- Filter sand and gravel are graded specifically for water filtration plants
- Filter sand and gravel can be used in municipal, industrial or residential application
- The spherical shape of uncrushed gravel promotes good flow and even distribution

PHYSICAL PROPERTIES

Filter Sand and Gravel

- Color: Light tan to reddish brown
- Density: 100 lbs./cu. ft.
- Mesh Size 18 x 35*
- Effective Size: 0.45-0.55 mm*
- Uniformity Coefficient: 1.6 or less*
- Acid Solubility: 0.3-1.6%
- Specific Gravity: 2.65-2.75

CONDITIONS FOR OPERATION

Filter Sand and Gravel

- Bed depth: 18-30 in.
- Freeboard: % of bed depth (min.)
- Backwash flow rate: 15-20 gpm/sq. ft.
- Backwash bed expansion: 20% of bed depth
- Service flow rate:
 - Municipal: 1.5-2 gpm/sq. ft.
 - Industrial: 3 gpm/sq. ft.
 - Domestic: 5 gpm/sq. ft.

*All physical properties and conditions for operation are the same for gravel with the exception of mesh size, effective size and uniformity coefficient.

Filter sand and gravel are naturally occurring, river washed, glacial deposit products. Their excellent chemical properties - high in silica content and low in soluble calcium, magnesium and iron compounds - meet AWWA-B100-96 specifications. Precision sizing and uniform grading to close limits meet the rigid specifications of professional engineers throughout the world.

Processing and regular analysis of production are supervised by registered professional engineers.

Filter sand and gravel are graded specifically for water filtration plants. It can be used in municipal, industrial or residential applications for sediment filtration.

Uncrushed gravel has a highly spherical shape that promotes good flow and even distribution in support beds. Gravel is low in soluble impurities and it will maintain the quality of the treated water, especially in softeners. Three inch layers are recommended in graded support beds.

